

PRODUCT CHEMICAL RESISTANCE

	Conc. (%)	Temp. Deg C	Resistance	
ACETIC ACID, Glacial C.P.	99	23	PR	
ACETIC ACID, (aquepus)	25	60	R	
	50	60	R	
ACRYLONITRILE	100	20	R	
	100	60	R	
ACETONE	100	23	NR	
AMMONIA	35	23	R	
ALLYL BROMIDE	100	23	NR	
AMMONIUM CHLORIDE	10	40	R	
	10	60	R	
	Sat.	60	R	
AMMONIUM SULFATEX	10	40	R	
	10	60	R	
	Sat.	60	R	
AMMONIUM SULFIDE	35	23	PR	
AMMONIUM THIOGLYCOLATE	100	23	R	
2-AMY CINNAMIC ALDEHYDE	100	23	NR	
BENZENE	100	20	PR	***
	100	60	NR	***
BENZOCYANAMIDE	100	23		
BENZOTRICHLORIDE	100	23	NR	***
2-BROMO PYRIDINE	100	23	NR	
CALCIUM CHLORIDE	10	20	R	
	10	60	R	
	Sat.	60	R	
CALCIUM THIOCYANATE	60	23	R	
CARBON TETRACHLORIDE	100	23	NR	***
CHROMIC ACID	25	20	R	
(aqueous)	25	60	R	
	80	20	R	
	80	60	R	
CITRIC ACID	10	40	R	
(aqueous)	10	60	R	
	Sat.	60	R	
CREOSOTE	100	23	NR	***
(Hardwood)				
CYCLOHEXINOL	100	20	R	
	100	60	R	
DETERGENT	100	20	R	
(Liquid)	100	60	R	
DIESEL OIL	100	20	R	
	100	60	PR	***
ETHYL ACETATE	100	22	PR	
ETHYL ALCOHOL	95	23	PR	
ETHYLENE DICHLORIDE	100	23	NR	***
ETHYLENE GLYCOL	100	20	R	
	100	60	R	
FORMALDEHYDE	40	20	R	
	40	60	R	
FORMIC ACID	90	23	PR	
GASOLINE	100	23	NR	***
GUAICOL	100	23	NR	***
GLYCERINE	100	20	R	
	100	60	R	
HYDROCHLORIC ACID C.P.	20	23	R	
	26	23	R	
	30	20	R	
	31	23	R	
	38	23	PR	
	43	20	PR	
	43	60	NR	
HYDRIDIC ACID	45	23	R	
HEPTANE	100	23	NR	***
HYDROGEN PEROXIDE	20	20	R	
	20	60	R	
	30	20	R	
	30	60	R	
	90	20	R	
	90	60	NR	



4039 Calle Platino Suite F
Oceanside CA 92056
Phone 760-643-1756
Fax 760-643-1757

	Conc. (%)	Temp. Deg C	Resistance	
ISOPROPANAL	100	20	R	
	100	60	R	
KEROSENE	100	23	NR	*
LACTIC ACID	10	20	R	
	10	60	R	
METAL CUTTING OILS	100	20	R	
	100	60	PR	
MINERAL OIL				
METHYL ETHYL KETONE	100	23	NR	
MOTOR OIL SAE 20	100	20	R	
	100	23	R	
NAPHTHA	100	20	R	
	100	60	PR	***
NICOTINE ETHYL AMID	100	23	PR	
NICKEL SULFATE	10	40	R	
	10	60	R	
	Sat.	60	R	
NITRIC ACID C.P.	30	20	R	
	30	60	R	
	50	20	R	
	67	23	PR	
	95	23	NR(d)	
OLEIC ACID	Sat.	30	R	
	Sat.	60	PR	
PARALDEHYDE U.S.P.	100	23	NR	
PERCHLORIC ACID	70	23	PR	
	60	23	R	
PERACETIC ACID	50	20	NR	
PHENOL	100	20	R	
	100	60	R(d)	
PHENYL ISOCYANATE	100	23	NR	
PHOSPHORIC ACID	85	23	R	
POTASSIUM CYANIDE	10	60	R	
	Sat.	60	R	
SODIUM CHLORIDE	10	20	R	
(Table Salt)	10	60	R	
	Sat.	60	R	
SODIUM HYPOCHLORITE	12	23	R	
SODIUM HYDROXIDE	30	20	R	
	30	60	R	
	50	20	R	
	50	60	R	
SULFURIC ACID C.P.	3	23	R	
	30	23	R	
	35	23	R	
	78-98	23-60	NR	
SULFUROUS ACID	6	23	R	
SUGAR SYRUP	50	20	R	
	50	60	R	
TOLUENE	100	23	NR	***
TRICHOETHYLENE	50	23	NR	***
TURPENTINE	12	23	NR	***
UREA	10	40	R	
(Aqueus)	10	60	R	
	33	60	R	
VEGETABLE OIL				***
<p>(R) RESISTANT 2.5% Change in weight or swell (PR) PARTIALLY RESISTANT 2.5 - 7% Change in weight or swell (NR) NOT RESISTANT 7% Change in weight or swell (d) SAMPLE DISCOLORS</p> <p>These values are obtained from laboratory prepared specimens and may not be exactly duplicated in commercial practice.</p>				